

# Polyglaze®

## PZ 200 XT & PZ W200 XT

## MULTIPURPOSE ADHESIVE FOR TILE & STONE

### PRODUCT DESCRIPTION

Polyglaze PZ 200 XT / PZ W200 XT is a premium multipurpose grey / white cement-based adhesive. It is a high performance polymer modified adhesive suitable for both internal and external applications. It is ideal for tile on tile application, large format tiles, ceramic / vitrified tiles/ precast terrazzo and wide varieties of natural stones.

### SUITABLE SUBSTRATES

- ◆ New and old concrete surfaces
- ◆ Cement screeds and mortar beds
- ◆ Concrete and concrete masonry
- ◆ Mivan / shear walls
- ◆ PCC and IPS flooring
- ◆ Plastered surfaces
- ◆ Bricks and AAC blocks masonry

### AREAS OF APPLICATION

- ◆ Interior floors and walls and exterior floors
- ◆ Residential and commercial application
- ◆ Levelled surfaces including bathrooms, balconies, kitchen areas.
- ◆ Ideal for tile-on-tile application

### ADVANTAGES

- ◆ Specially designed with extended open time
- ◆ Single component - just add water, mix easily and apply
- ◆ Durable with high tensile adhesion strength
- ◆ Can be used in damp areas with necessary precautions
- ◆ Being ready to use, the product saves considerable time and labour

### STANDARDS

- ◆ IS 15477: 2019 Classified as Type 2T
- ◆ EN 12004 and ISO 13007 Classified as C2TE

### APPLICATION METHODOLOGY

#### Surface Preparation

- ◆ The surface should be clean, dry, free from dust, grease, oil, and other contaminants
- ◆ The surface should be properly levelled for best results; in case of undulations or damage, correct the substrate at least 48 hours before application
- ◆ Allow concrete floors and walls to cure and dry for at least 3 - 4 weeks prior to tiling

#### Mixing

- ◆ Take 4.2 L to 4.6 L of clean water (approx. 21-23% by weight) in a bucket and gradually add 20Kg of Polyglaze PZ 200 XT or PZW 200 XT while mixing continuously



- ◆ Mixing can be done mechanically by stirrer or manually by hand
- ◆ Mix thoroughly until a homogeneous, lump-free paste is achieved, ensuring no lumps or unmixed material remain
- ◆ Let the paste rest for 5 - 10 minutes for polymeric dispersion
- ◆ The paste should be kept away from direct sunlight and heat

#### Tile Fixing

- ◆ Before fixing the tiles or stones, clean their backsides with wet cloth to remove all dust particles
- ◆ Use a proper size notched trowel to ensure full bedding of the tile or stone
- ◆ Screeding / Plastering prior to application is a must
- ◆ Apply the mixed paste onto the surface using the straight edge of the trowel. Then run the notched side of the trowel to achieve the desired thickness
- ◆ Before placing the tiles, apply a layer of adhesive to the back of the tiles using notched trowel and press firmly to the substrate. Then knock properly all around with a rubber hammer in order to spread the adhesive equally for a good contact
- ◆ For large format tiles and stones, back buttering is necessary to ensure full bedding and firm support
- ◆ Ensure a gap is maintained between adjacent tiles using spacers to allow for thermal expansion and achieve uniform joint width
- ◆ Any adjustment should be done within 20 - 25 minutes before the paste starts hardening
- ◆ Carefully remove any excess paste immediately from the joints and the face of the tiles

## Grouting & Cleaning

- ◆ Once tiles are laid, remove excess / loose material with sponge and clean water
- ◆ Grouting must be done after 24 hours for better results
- ◆ If opting for a cementitious grout, use PZC Tile Grout mixed with either clean water or PZ TG Admix (400 ml for 10 kg material)
- ◆ If opting for a Stain-Free epoxy grout then use PZ SF Epoxy Grout or PZ 2K Epoxy Grout
- ◆ Clean the tools with water immediately after use

## PACKAGING

- ◆ Polyglaze PZ 200 XT and PZ W200 XT are available in 20kg and 40kg BOPP bags

## STORAGE & SHELF LIFE

- ◆ Store in a dry place away from moisture and sunlight
- ◆ Best before 12 months from the manufacturing date in original sealed condition

## PRECAUTIONS AND LIMITATIONS

- ◆ Tiling should be avoided during very hot or rainy weather conditions
- ◆ Always use clean, potable water for mixing
- ◆ Avoid using high-speed mixing when using electric mixing equipment
- ◆ Always add powder to water (not water to powder) to prevent lump formation
- ◆ Do not exceed the recommended water ratio; never add extra water
- ◆ Do not add cement, sand, or any additives to the tile adhesive
- ◆ Do not exceed the bed thickness of 12mm
- ◆ Follow the specified pot life and open time for optimal results
- ◆ Protect the tiled surface from direct sunlight and rain for at least 24 hours after application

## HEALTH & SAFETY

- ◆ Use a respiratory mask and protective gloves during application.
- ◆ Clean hands with soap and water after application.
- ◆ Avoid contact with skin / eyes. In case of unlikely contact, rinse eyes immediately with plenty of clean water and cleanse skin with soap and lukewarm water. Seek medical advice if irritation occurs / persists.
- ◆ In case of unlikely swallowing, seek medical attention immediately.



### Disclaimer:

The information in this TDS is for general guidance only. Specific advice for site conditions is available upon request. Details provided by the company are in good faith, when product is properly stored, handled, and applied under normal conditions. The site conditions, material compatibility, and workmanship are beyond our control, no warranties expressed or implied are given. The company accepts no liability for unsatisfactory results or consequential damages arising from product use.



**EVERSHINE BUILD INDIA PRIVATE LIMITED**

An ISO 9001 : 2015 Certified Company

Regd. Off. : Plot No. 77, EPIP, TSIC Pashamylaram, Isnapur,  
Patancheru Mandal, Sangareddy Dist., Hyderabad 502 307, Telangana

☎ 1800-425-0699 (Toll free) | 🌐 [www.evershinebuild.com](http://www.evershinebuild.com) | ✉ [info@evershinebuild.com](mailto:info@evershinebuild.com)



# TECHNICAL DATA SHEET

## PHYSICAL PROPERTIES

Physical Appearance	Dry Powder
Colour	Grey and White
Water Mixing Ratio	Approx. 21 - 23% by weight
Pot Life	Approx. 3 - 4 hrs
Open Time	Approx. 25 minutes
Adjustability Time	Approx. 30 minutes
Setting Time	24 hrs
Time to foot traffic	24 hrs
Grouting Time	24 hrs
Working Temperature	10° C to 40° C

## PERFORMANCE PROPERTIES

As per IS 15477 : 2019 Classified Type 2T Adhesive

PROPERTIES		IS REQUIREMENT	PZ 200XT / PZ W200XT
Tensile adhesion strength	Dry condition (28 days)	Min. 1.0 N/mm <sup>2</sup>	1.25 - 1.50 N/mm <sup>2</sup>
	Wet condition (28 days)	Min. 1.0 N/mm <sup>2</sup>	1.14 - 1.40 N/mm <sup>2</sup>
Shear adhesion strength	Dry condition (28 days)	Min. 1.25 N/mm <sup>2</sup>	1.30 - 1.45 N/mm <sup>2</sup>
	Heat Ageing (28 days)	Min. 1.0 N/mm <sup>2</sup>	1.10 - 1.15 N/mm <sup>2</sup>
	Wet Condition (28 days)	Min. 1.0 N/mm <sup>2</sup>	1.15 - 1.25 N/mm <sup>2</sup>
Slip (mm)		Max. 0.5 mm	0.20 - 0.30 mm

As per EN 12004 : 2017 / ISO 13007 Classified C2TE

PROPERTIES		EN / ISO REQUIREMENT	PZ 200XT / PZ W200XT
Tensile adhesion strength	Initial / Dry condition @ 28 days	>1.0 N/mm <sup>2</sup>	1.25 - 1.50 N/mm <sup>2</sup>
	Water immersion @ 28 days	>1.0 N/mm <sup>2</sup>	1.14 - 1.40 N/mm <sup>2</sup>
	Heat ageing @ 28 days	>1.0 N/mm <sup>2</sup>	1.0 - 1.25 N/mm <sup>2</sup>
	Freeze thaw @ 28 days	>1.0 N/mm <sup>2</sup>	1.25 - 1.40 N/mm <sup>2</sup>

## COVERAGE

For a bed thickness of 3 - 4 mm (6mmx6mm Square - Notched trowel)	Approx. 50 - 60 Sq.ft / 20kg bag
---	----------------------------------

Note :

- ◆ Coverage will vary depending on the surface and the application method.
- ◆ All the above values are based on testing conducted at 27 ± 2°C and relative humidity of 65 ± 5%. Actual results may vary depending on specific site conditions such as weather, surface and application method.